

Synthesis of Mn(II) Complexes- Carboxymethyl Chitosan Schiff Base Salicylaldehyde and Antibacterial Activity

by Nor Basid Adiwibawa Prasetya

Submission date: 23-May-2023 10:00AM (UTC+0700)

Submission ID: 2099738852

File name: alensi_-_Synthesis_of_Mn_II_Complexes-Carboxymethyl_Chitosan.pdf (1.1M)

Word count: 5980

Character count: 32905

Synthesis of Mn(II) Complexes-Carboxymethyl Chitosan Schiff Base Salicylaldehyde and Antibacterial Activity

Ismiyarto*, Niken Windi Saputri, Liswinda Zafirah Rahmatia, Purbowatiningrum Ria Sarjono, Ngadiwiyana, Nor Basid Adiwibawa Prasetya, Damar Nurwahyu Bima

¹⁷ Department of Chemistry, Faculty of Science and Mathematics, Diponegoro University
Jl. Prof. H. Soedarto SH Tembalang, Semarang 50275, Indonesia

*Corresponding author: ismiyarto@live.undip.ac.id

Received: February 2021; Revision: April 2021; Accepted: May 2021; Available online: June 2021

Abstract

The development of compounds with a better antibacterial activity is highly needed. One way to achieve this is by modifying the structure of the compound using chitosan as a starting material, because of its abundant natural source in Indonesia⁴⁶, its biodegradable properties, and its structure where free amines are present. This study aims to obtain ⁴Mn(II) -Carboxymethyl Chitosan Schiff Base-Salicylaldehyde complex to increase its antibacterial activity against *Staphylococcus aureus* (Gram positive) and *Escherichia coli* (Gram negative). Schiff Base carboxymethyl chitosan-salicylaldehyde was synthesized from carboxymethyl chitosan with salicylaldehyde. Next, the Schiff Base Carboxymethyl Chitosan-Salicylaldehyde was complexed with $MnCl_2 \cdot 4H_2O$ and then characterized by FTIR, UV-Vis Spectrophotometer, and AAS and tested for antibacterial activity with the disc diffusion method against *Staphylococcus aureus* and *Escherichia coli*. The product of Carboxymethyl Chitosan Schiff Base-salicylaldehyde is a brownish yellow solid with a yield of 64% (w/w) and has antibacterial activity against *Staphylococcus aureus* (clear zone diameter 11 mm) and *Escherichia coli* (clear zone diameter 13 mm). The product of Mn(II) Complexes-Carboxymethyl Chitosan Schiff Base-salicylaldehyde is a black solid with a yield of 59% (w/w) and has antibacterial activity against *Staphylococcus aureus* (clear zone diameter 13 mm) and *Escherichia coli* (clear zone diameter 17 mm).

Keywords: Antibacterial activity, carboxymethyl chitosan, Mn(II) complexes, schiff base

DOI: 10.15408/jkv.v7i1.19866

1. INTRODUCTION

One attempt to overcome health problems caused by bacteria is the development of antibacterial compounds with a better antibacterial activity. One of the compounds that can be used as antibacterial is chitosan, which is a modification of chitin that is abundant in nature (Shanmugam *et al.*, 2016), and is the largest structural component of crustacean skin found in shrimps and crabs, also found on walls of fungal cells (Kurozumi *et al.*, 2019). Chitosan is also biocompatible, biodegradable, non-toxic, non-immunogenic and non-carcinogenic; therefore, chitosan has prospective applications in various fields such as biomedicine and wastewater treatment (Al-Issa *et al.*, 2017). Chitosan is a cationic polymer, so it can interact with phospholipids from the negatively charged Gram negative

bacterial cell walls (Yin *et al.*, 2012). As a result, chitosan has better antibacterial activity against Gram negative bacteria than Gram positive because the cell walls of Gram positive bacteria do not contain phospholipids (Fouda *et al.*, 2013).

Chitosan has low solubility in water, which limits its overall usefulness (Darmokoesoemo *et al.*, 2018). To overcome these limitations, chemical modification of chitosan is carried out, one example is carboxymethyl chitosan (Rahmani *et al.*, 2016). Carboxymethyl chitosan is formed from the carboxymethylation reaction with monochloroacetic acid. Carboxymethyl chitosan has a higher water solubility than chitosan, so it is expected to have better antibacterial activity than chitosan, where the -COOH group on carboxymethyl chitosan can

form a hydrogen bond with the hydrophilic part of the bacterial cell membrane (Fei Liu *et al.*, 2001). In addition, chitosan has a primary imine group so that it can be modified to become a Schiff bases. Schiff bases are compounds that have an imine functional group ($>C=N-$) (Tamer *et al.*, 2016), where the group has a lone pair on N which can form hydrogen bonds with the hydrophilic part of the bacterial membrane (Nworie *et al.*, 2016). Schiff bases have lone pairs that can be donated to a central atom in the formation of complexes with metal Mn. Mn metal has biocompatible properties, where small amounts of Mn plays a role in biochemical reactions in the body, therefore Mn metal can be applied in the biomedical world (Ali & Iqbal, 2017). Metal atoms easily lose electrons and form positively charged ions which are easily dissolved in biological fluids. The formation of positive ions makes it easier to interact with electron-rich biomolecules such as DNA. On the other hand, metal-ligand combinations make it possible to design new entities with various physical properties and chemical reactivity, which includes charge, solubility, rate of ligand exchange, strength of metal-ligand bonds, Lewis acidity, and ligand conformation. Therefore, compared to organic pharmaceuticals, the structural and electronic properties of complex compounds are of great interest in medicinal chemistry developments, especially as antimicrobial agents with new methods of action to treat diseases that are already drug resistant (Claudel *et al.*, 2020).

Previous research has been carried out on the synthesis of Schiff base carboxymethyl chitosan-salicylaldehyde and its antibacterial activity test by Abdel-Monem *et al.*, (2020). Research on the formation of the Mn(II)-base Schiff carboxymethyl chitosan-salicylaldehyde complex as a result of the reaction between the Schiff carboxymethyl chitosan-salicylaldehyde base with $MnCl_2 \cdot 4H_2O$ has never been reported. It is expected that the Mn(II)-Schiff base carboxymethyl chitosan-salicylaldehyde complex has a better antibacterial activity than chitosan and other chitosan derivatives.

2. MATERIALS AND METHODS

Tools and Materials

The tools used in this study were a research standard glass instrument, a Ubbelohde viscometer, a reflux device, an analytical balance, Laminar Air Flow, a

Memmert IN55 incubator, an orbital shaker, autoclave, 10-100 μ L micro pipette, ose needle, petri dish, spreader, tweezers, Hitachi UH5300 UV-Vis (Ultraviolet-Visible) spectrophotometer, Shimadzu Prestige 21 Fourier Transform Infrared (FTIR) spectrophotometer, and Perkin-elmer Analyzer 100 Atomic Absorption Spectrophotometer (AAS).

The materials used in this study were salicylaldehyde p.a (Merck), chitosan (Chimultiguna), monochloroacetic acid (Merck), isopropanol (Brataco), glacial acetic acid p.a (Merck), NaOH (Merck), $MnCl_2 \cdot 4H_2O$ (Merck), ethanol p.a. (Merck), distilled water, nutrient agar (Merck), peptone (Merck), yeast extract (Merck), Whatman filter paper No. 42, universal indicator, amoxicillin, and 70% alcohol.

Procedure

This research begins with the identification of commercial chitosan used, followed by the synthesis of carboxymethyl chitosan by reacting chitosan with monochloroacetic acid, then the analysis by FTIR and test for antibacterial activity. Next, the synthesis of the Schiff carboxymethyl chitosan-salicylaldehyde base and the Schiff carboxymethyl chitosan-benzaldehyde base was carried out, followed by analysis with UV-Vis, FTIR spectrophotometry and antibacterial tests. After that, the Schiff base carboxymethyl chitosan-salicylaldehyde was complexed with $MnCl_2 \cdot 4H_2O$ and the product was analyzed by spectrophotometry UV-Vision, FTIR and AAS and tested for its antibacterial activity.

Identification of Chitosan Used for Synthesis Determination of the Degree of Deacetylation

Chitosan, which will be used for synthesis was analyzed by infrared spectrophotometry. Using the infrared spectra, the degree of deacetylation (DD%) can be calculated with the base line method, by comparing the absorbance in the wavenumber of the N-acetyl group ($1650-1500\text{ cm}^{-1}$ (A_{1655})) with the absorbance at the NH_2 group wave number ($3500-3430\text{ cm}^{-1}$ (A_{3450})). From the FTIR spectra of chitosan, the degree of deacetylation was determined using the base line method.




Figure 1. IR spectra for the determination of the degree of deacetylation using the base line method from the graph above, the degree of deacetylation is determined by the formula $\%DD = 100 - \left[\left(\frac{A_{1652}}{A_{3401}} \right) \times \frac{100}{1.33} \right]$ (Khan *et al.*, 2002)

Where % DD is the degree of deacetylation, A_{1652} is the carbonyl absorption of the amide, A_{3401} is the hydroxyl absorption used as the internal standard and the value of 1.33 is the ratio of A_{1655} and A_{3401} in the complete deacetylation process.

Molecular Weight Determination

The determination of the molecular weight was carried out by the viscometrical method. 1 g of chitosan is dissolved in a mixture of acetic acid and NaCl solution in a ratio of 3:1. The concentration of chitosan solution was varied to 0.1%; 0.2%; 0.3% and 0.4% and 0.5%. After that, the flow time was measured with the Ubelohde Viscometer. Then, the determination of the molecular weight was carried out using the Marck-Houwink equation.

Synthesis of Carboxymethyl Chitosan (Darmokoesoemo *et al.*, 2018)

Three mole variations of monochloroacetic acid 3.25; 4.23; and 9.10 mmol in different three-neck flask was dissolved with 2 mL of isopropanol, then the solution is added slowly into 1 g of chitosan (6.12 mmol) which has been dissolved with 40

mL of 16% (v/v) acetic acid and 1.35 g of NaOH was added. The solution mixture was stirred and heated at 50 °C for 4 hours. The product is precipitated with ethanol. The precipitate obtained was filtered with a Buechner funnel and washed with distilled water and 70% ethanol, then dried at a temperature of 50-80 °C. Each carboxymethyl chitosan was analyzed by FTIR spectrophotometry and tested for its antibacterial properties.

Synthesis of Schiff Base Carboxymethyl Chitosan-Salicylaldehyde (Darmokoesoemo *et al.*, 2018)

Schiff's base was synthesized by reacting 1 g of carboxymethyl chitosan (CMC) the result was then dissolved in 20 mL of 2% acetic acid with 0.00137 mol of salicylaldehyde or 0.00147 mol of benzaldehyde (benzaldehyde was used as a comparison to determine the effect of substituents in benzene on antibacterial activity) in ethanol (1:1). Then the mixture was refluxed at 50-60 °C for 5 hours, then precipitated using 5% NaOH. The precipitate is filtered over a Buechner funnel and washed with distilled water and ethanol and dried

using an oven at 50 °C. The product was characterized by UV-Vis spectrophotometry (2% acetic acid solvent), FTIR spectrophotometry and tested for its antibacterial activity.

Synthesis of the Complex of Mn(II) - Schiff Base Carboxymethyl Chitosan-Salicylaldehyde (Barbosa *et al.*, 2017)

The Schiff base complex was obtained by reacting 0.2 g Schiff base carboxymethyl chitosan-salicylaldehyde and the synthesized result was then dissolved in 20 mL 2% acetic acid and 0.27 g (0.00136 mol) $\text{MnCl}_2 \cdot 4\text{H}_2\text{O}$ in 20 mL ethanol solvent which was added slowly into an alkaline Schiff carboxymethyl chitosan-salicylaldehyde solution. The mol ratio of Schiff base carboxymethyl chitosan-salicylaldehyde with $\text{MnCl}_2 \cdot 4\text{H}_2\text{O}$ is 1:1. The mixture was stirred and heated for 6 hours at 60°C. The resulting product was precipitated using 5% NaOH then the precipitate was filtered. The residue was then washed with distilled water and ethanol and then oven dried. The reaction product was characterized by UV-Vis spectrophotometry (2% acetic acid solvent), FTIR, AAS spectrophotometry and tested for their antibacterial activity.

Antibacterial Activity Test

As much as 1 g of nutrient agar is dissolved in 50 mL of distilled water containing 0.025 g of yeast extract and 0.125 g of peptone. The mixture was stirred and then sterilized using an autoclave for 45 minutes together with a needle and a test tube. Bacteria implantation is carried out in Laminar Air Flow. The agar medium was inserted into the test tube and placed at a slope of $\pm 30^\circ$. Colonies of *Staphylococcus aureus* and *Escherichia coli* bacteria were planted into the media so that it tilted in the test tube by scratching with a loop needle. The results of planting the bacteria were incubated for 24 hours.

Making Bacterial Inoculum

A total of 0.05 g of yeast extract and 0.25 g of peptone were dissolved in 100 mL of distilled water. The mixture was stirred and put into three erlenmeyers then sterilized using an autoclave for 45 minutes with a loop needle. Bacterial stocks that have been incubated for 24 hours were suspended in the nutrient broth media. The bacterial suspension was incubated

for 2 hours in a shaker incubator and the absorbance measurement was carried out every 2 hours at a wavelength of 600 nm to obtain the same bacterial suspension turbidity with the standard solution turbidity of 0.5 McFarland scale.

Test Compound Solution Preparation

The test solution was prepared by dissolving 1 mg of three samples of carboxymethyl chitosan, chitosan, Schiff base carboxymethyl chitosan-benzaldehyde, Schiff base carboxymethyl chitosan-salicylaldehyde and Mn(II)-Schiff base carboxymethyl chitosan-salicylaldehyde complex in 10 mL of 2% acetic acid solution to make a concentration 100 μg / mL. Acetic acid 2% was used as a negative control and amoxicillin was used as a positive control.

Making the Media for The Test

A total of 0.05 g of yeast extract and 0.25 g of peptone and 2 g of nutrient agar are dissolved in 100 mL of distilled water. The mixture was stirred until homogeneous, then sterilized using an autoclave for 45 minutes along with a petri dish. Then 20 mL of nutrient media was poured into the petri dish and then left to allow the nutrient media to solidify.

Antibacterial Activity Test

The bacterial suspension that had met the turbidity of the standard solution with a concentration of 0.5 McFarland was inoculated onto 40 μL of solid agar media. A total of 10 μL of the test solution was dropped on to disc paper until the test solution was completely diffused. The disc paper was then placed on the surface of the nutrient media so that it was used as a test medium for further incubation of 24 hours, and observations were made at 8, 12, and 18 hours. In this study, amoxicillin solution was used as a positive control and acetic acid solution was used as a negative control. The visible zone is measured in diameter in millimeters.

3. RESULT AND DISCUSSION

Identification of Chitosan to be Used in the Synthesis

Determination of the Degree of Deacetylation

The degree of deacetylation of chitosan was determined based on FTIR spectral data using the base line method. From

the calculation, it was found that the deacetylation degree of chitosan used in this synthesis process was 76.95%, which means that 76.95% of the amide groups have been successfully hydrolyzed into free -NH_2 groups.

Molecular Weight Determination


In determining the molecular weight of chitosan, the graph equation is $y = 34143x + 122.02$ with a R^2 value of 0.9977. From this equation, it can be obtained that the intrinsic viscosity value is 122.02, so that according to the Mark-Houwink equation, the molecular weight of chitosan is 153846.348 Daltons. From these results it can be said that the chitosan used is a polymer with $n = 949$.

Synthesis of Carboxymethyl Chitosan

Carboxymethyl chitosan results from the reaction of monochloroacetic acid, with 3 variations of monochloroacetic acid 3.25; 4.23; and 9.10 mmol, produced 6.12 mmol chitosan in the form of a brownish yellow solid. Each carboxymethyl chitosan obtained was analyzed using FTIR spectrophotometry and tested for its antibacterial activity. The infrared spectrum of chitosan and three carboxymethyl chitosan products with monochloroacetic acid mol variations is shown in **Figure 2**. Chitosan

shows the absorption of the carbonyl group (>C=O) acetyl at the wave number 1652 cm^{-1} , while the carboxymethyl chitosan with 3 (mol) variations of monochloroacetic acid shows a shift in absorption to a higher wave number, with the wavenumber of 1660.00; 1669.00; and 1665.00 cm^{-1} which shows the presence of carbonyl uptake (>C=O) of carboxylates. This indicates that the carboxymethyl chitosan has been formed, which is indicated by the appearance of uptake (>C=O) of the carboxylate.

From the FTIR spectra, the degree of substitution was determined using the baseline method. The substitution degree of carboxymethyl chitosan was obtained resulting the mol variation of monochloroacetic acid 3.25; 4.23; and 9.10 mmol at 38.7%; 41.7% and 51.6%. This indicates that the more moles of monochloroacetic used, the more acetate groups that enter the chitosan framework. However, if too much monochloroacetic is used the chitosan framework becomes saturated due to steric hindrances. For this reason, the further substitution process is limited. The yield of the product obtained in the variation of monochloroacetic acid mol was 3.25; 4.23; and 9.10 mmol 43% each; 44%; and 37% (w/w).



Note =

- a : chitosan,
- b : CMC 1 (carboxymethyl chitosan with 3.25 mol monochloroacetic acid),
- c : CMC 2 (carboxymethyl chitosan with 4.23 mol monochloroacetic acid)
- d : CMC 3 (carboxymethyl chitosan with 9.10 mol monochloroacetic acid)

36

Figure 2. IR spectra of chitosan and carboxymethyl chitosan with three variations of moles

Synthesis of Aromatic Carboxymethyl Chitosan-Aldehyde Schiff Base

The synthesis of the Schiff base carboxymethyl chitosan-benzaldehyde and the Schiff base carboxymethyl chitosan-salicylaldehyde produced a brownish yellow solid with a yield of 54% and 64% (w/w). Synthesis of Schiff base carboxymethyl chitosan-benzaldehyde was carried out to determine the effect of the hydroxyl substituent on salicylaldehyde on the antibacterial activity of Schiff base. The Schiff base product was analyzed by UV-Vis spectrophotometry and compared the spectra with carboxymethyl chitosan. From the UV-Vis spectra, a widened peak was found which was possibly caused by the result of the overlapping of several peaks, due to that deconvolution was carried out to determine the overlapping peaks of each product. The peak of the deconvolution result is shown in Table 1.


Table 1. UV-Vis Peak deconvolution results

Produk	Peak (nm)		
	I	II	III
carboxymethyl chitosan	234	250	280
Schiff base carboxymethyl chitosan-benzaldehyde	236	266	352
Schiff base carboxymethyl chitosan-salicylaldehyde	230	270	386


The deconvolution of carboxymethyl chitosan produced 3 peaks. Firstly, in the 234 nm area ($\epsilon = 236.92$ L/cm.mol) which is the $n \rightarrow \sigma^*$ transition of the unconjugated chromophore group on chitosan. Next is in 250 nm which is a transition $\pi \rightarrow \pi^*$ ($\epsilon = 206.59$ L/cm.mol) carboxylic groups (COOH) and finally 280 nm ($\epsilon = 188.79$ L/cm.mol) which are transitions of $n \rightarrow \pi^*$ carboxylate groups (-COOH) (Figure 3a).

Deconvolution of the Schiff base carboxymethyl chitosan-benzaldehyde produces 3 peaks, at a wavelength of 236 nm ($\epsilon = 305.23$ L/cm.mol) which is an $n \rightarrow \sigma^*$ transition from the unconjugated chromophore group on chitosan, 266 nm ($\epsilon = 233, 85$ L/cm.mol) which is a transition $\pi \rightarrow \pi^*$ an imine group ($>C=N-$) which is conjugated with a double bond on the benzene group and 352 nm ($\epsilon = 100.57$ L/cm.mol) which is an $n \rightarrow \pi^*$ the imine group ($>C=N-$)


conjugated with a double bond to the benzene group (Figure 3b).



(a)



(b)



(c)

Figure 3. UV-Vis spectra deconvolution (a) carboxymethyl chitosan, (b) schiff base carboxymethyl chitosan-benzaldehyde, (c) schiff base carboxymethyl chitosan-salicylaldehyde. (peak I: peak at 236 nm which is the transition $n \rightarrow \sigma^*$, peak II: peak at 266 nm which is the transition $\pi \rightarrow \pi^*$ ($>C=N-$), peak III: peak at 352 nm which is the transition $n \rightarrow \pi^*$ the imine group ($>C=N-$))

Deconvolution of Schiff carboxymethyl chitosan-salicylaldehyde produces 3 peaks, namely at a wavelength of 230 nm ($\epsilon = 321.04 \text{ L / cm.mol}$) which is an $n \rightarrow \sigma^*$ transition from the unconjugated chromophore group on chitosan, 270 nm which is a transition $\pi \rightarrow \pi^*$ ($\epsilon = 246.93 \text{ L/cm.mol}$) the imine group ($>\text{C}=\text{N}-$) and the hydroxy group (OH) substituted benzene ring conjugation and 386 nm which is the transition $n \rightarrow \pi^*$ ($\epsilon = 76.38 \text{ L/cm.mol}$) imine groups ($>\text{C}=\text{N}$) and conjugated ring-substituted benzene (OH) groups (Figure 3c) (Ermis, 2018). There is a shift in wavelengths in bands II and III from the Schiff carboxymethyl chitosan-benzaldehyde base with the Schiff carboxymethyl chitosan-salicylaldehyde base due to the presence of hydroxyl substituents in salicylaldehyde resulting in a bathochromic shift (Tan *et al.*, 2017).




Figure 4. Infrared spectra of carboxymethyl chitosan, Schiff base carboxymethyl chitosan-benzaldehyde and carboxymethyl chitosan-salicylaldehyde (a:carboxymethyl chitosan, b:Schiff base carboxymethyl chitosan-benzaldehyde, c:Schiff base carboxymethyl chitosan-salicylaldehyde)

Further characterization using infrared spectrophotometry was carried out to determine the formation of groups ($>\text{C}=\text{N}-$) on the Schiff base. The infrared spectrum of carboxymethyl chitosan showed the presence of group absorption ($>\text{C}=\text{O}$) at the wave number 1660 cm^{-1} , while in the Schiff base carboxymethyl chitosan-benzaldehyde and

Schiff base carboxymethyl chitosan-salicylaldehyde showed a shift in absorption towards a smaller wave number, which are $1636, 5 \text{ cm}^{-1}$ and $1644, 5 \text{ cm}^{-1}$. The presence of this shift indicates that the Schiff base has been formed (Barbosa *et al.*, 2017). The infrared spectra of carboxymethyl chitosan and Schiff's base are shown in Figure 4.

Complex Synthesis of Mn(II) -Base Schiff Carboxymethyl Chitosan-Salicylaldehyde

The synthesis of Mn(II)-Schiff base carboxymethyl chitosan-salicylaldehyde complex was obtained by reacting the Schiff base carboxymethyl chitosan-salicylaldehyde with $\text{MnCl}_2 \cdot 4\text{H}_2\text{O}$. Complexes of Mn(II)-base Schiff carboxymethyl chitosan-salicylaldehyde in the form of a brownish black solid with a yield of 59% (w/w).




Figure 5. Schiff base products carboxymethyl chitosan-salicylaldehyde (a) and Mn(II)-Schiff base carboxymethyl chitosan-salicylaldehyde complex (b)

The Schiff base complex can be formed because of the coordination bond that occurs between the $\text{C}=\text{N}$ group and the OH group on the Schiff base carboxymethyl chitosan – salicylaldehyde with Mn metal (Iftikhar, 2018). The lone pair present on the N atom of the $\text{C}=\text{N}$ group and the O atom in the OH group causes the Schiff base to act as a ligand by donating its lone pair to the Mn ion which acts as the central metal ion (Malekshah *et al.*, 2020).




Figure 6. The reaction for the formation of the Mn(II)-Schiff base carboxymethyl chitosan-salicylaldehyde complex




Figure 7. UV-Vis spectra deconvolution of Mn(II)-Schiff base carboxymethyl chitosan-salicylaldehyde complex. (Peak I: peak at 236 nm which is the transition $n \rightarrow \sigma^*$, Peak II: peak at 266 nm which is the transition $\pi \rightarrow \pi^*$ ($>C=N-$), Peak III: peak at 352 nm which is the transition $n \rightarrow \pi^*$ imine group ($>C=N-$), Peak IV: peak at 422 nm which is a transition in the Mn complex formed)

According to Martak (2018), $MnCl_2 \cdot 4H_2O$ has a maximum wavelength of 286 nm. The formation of the complex causes the formation of peaks in the UV-Vis spectra at a larger wavelength (bathochromic) of 422 nm ($\epsilon = 163.51 \text{ L / cm.mol}$), indicating that the complex has been formed (Keypour *et al.*, 2017). The deconvolution of the UV-Vis

spectra of the Mn(II) - Schiff base carboxymethyl chitosan-salicylaldehyde complex is shown in **Figure 7**.

Further characterization was carried out using an infrared spectrophotometer to confirm the formation of the complex Mn(II)-Schiff base carboxymethyl chitosan-salicylaldehyde complex. Analysis with an infrared spectrophotometer gives the spectra shown in **Figure 8**.

The infrared spectrum of the Mn(II) complex, Mn(II) Schiff base carboxymethyl chitosan-salicylaldehyde, shows a shift in the absorption of the imine group ($>C=N-$) towards a lower wavenumber, 1571.94 cm^{-1} , which indicates the coordination of the Schiff base with the central metal ion. The typical peak of complex compounds is seen in the fingerprint area, which shows the absorptions at the wavenumber of 442 cm^{-1} and 576 cm^{-1} as Mn-O and Mn-N groups (Kanmani *et al.*, 2016). Mn-O and Mn-N absorption has a low intensity, this is because both are coordinating covalent bonds, where the bond strength is weaker than polar covalent bonds (Sastrohamidjojo, 2001). In addition, the absorption of the two groups is in the fingerprint area, so to find out more about the presence of Mn in the sample characterization was also done using AAS.




Figure 8. IR spectra of Mn(II)-Schiff base carboxymethyl chitosan-salicylaldehyde complex (a: Schiff base carboxymethyl chitosan-salicylaldehyde and b: Mn(II) Schiff base carboxymethyl chitosan-salicylaldehyde complex)

Furthermore, to determine the level of Mn in the sample, characterization was carried out using AAS. Stoichiometrically, the Mn content in the sample was 13.69% and from the results of characterization using AAS, the Mn content in the sample was 12.74%.

Antibacterial Activity Test

The clear zone diameter in this antibacterial activity test was measured at an

incubation time of 12 hours. The results of the antibacterial activity test of carboxymethyl chitosan (CMC) with the best antibacterial activity can be seen in Table 2 (first experiment).

In general, the results of the antibacterial activity test of chitosan and carboxymethyl chitosan produced a larger clear zone against Gram negative bacteria (*Escherichia coli*) than Gram positive bacteria (*Staphylococcus aureus*). These data indicate that, in general, samples have a higher sensitivity to *Escherichia coli* bacteria than *Staphylococcus aureus* bacteria. The different sensitivity of carboxymethyl chitosan to *Escherichia coli* and *Staphylococcus aureus* is due to differences in the cell membrane structure of each bacteria (Fouda *et al.*, 2013). The difference in the cell membrane structure of *Escherichia coli* and *Staphylococcus aureus* can be seen from the component of the outer membrane and the layer of the cell walls. The cell wall of *Staphylococcus aureus* bacteria is composed of several layers of peptidoglycan to form a thick and rigid structure that makes these bacterial cells difficult to penetrate (Silhavy *et al.*, 2010).

Table 2. The results of the antibacterial activity test results for CMC, BS CMC 1-aromatic aldehyde and Mn(II)-Schiff base carboxymethyl chitosan-salicylaldehyde complex

No	Compound	concentration (ppm)	Clear zone (mm)					
			Staphylococcus aureus			Escherichia coli		
			Test			Test		
			I	II	III	I	II	III
1	Chitosan	100	12	10	-	13	11	-
2	CMC 1	100	14	11	11	15	13	13
3	CMC 2	100	12	-	-	13	-	-
4	CMC 3	100	8	-	-	7	-	-
5	BS CMC 1-benzaldehyde	100	-	11	11	-	13	14
6	BS CMC 1-salicylaldehyde	100	-	15	12	-	16	14
7	Mn(II)-BS CMC 1-salicylaldehyde complex	100	-	-	13	-	-	17
8	Amoxicillin (+)	30	20	15	13	23	24	18
9	Acetate acid (-)	2000	11	8	7	12	10	8

Note:

The results of the antibacterial activity test were observed with an incubation time of 12 hours.

CMC 1, (carboxymethyl chitosan, monochloroacetic acid (3.25 mmol)

CMC 2, (carboxymethyl chitosan, monochloroacetic acid (4.23 mmol)

CMC 3, (carboxymethyl chitosan, monochloroacetic acid (4.91 mmol)

BS CMC 1-benzaldehyde = Schiff base carboxymethyl chitosan-benzaldehyde

BS CMC 1-salicylaldehyde = Schiff base carboxymethyl chitosan-salicylaldehyde.

Mn(II)-BS CMC 1-salicylaldehyde complex = Mn(II)-Schiff base carboxymethyl chitosan-salicylaldehyde complex)

In *Escherichia coli*, the cell wall consists of a thin peptidoglycan and an outer membrane composed of lipopolysaccharides and phospholipids. Lipopolysaccharides have hydrophilic and hydrophobic groups (Miller and Salama, 2018). The hydrophilic part can form hydrogen bonds with the carboxylate group of carboxymethyl chitosan so that it can penetrate the lipopolysaccharide layer of the outer membrane of the bacterial cell.

Based on the data in **Table 2** (the first experiment), from the results of the antibacterial activity test, it is known that carboxymethyl chitosan with a variation of 3.25 mmol of monochloroacetic acid mol (CMC 1) has a stronger antibacterial activity than chitosan, this is due to the modification of chitosan to carboxymethyl chitosan which has a carboxylic group (-COOH). It can be seen that the mol variation of monochloroacetic acid is 4.23 mmol (CMC 2) and 4.91 mmol (CMC 3), in general, there is a decrease in antibacterial activity due to an increase in molecular weight which makes it difficult for antibacterial compounds to diffuse (Yin *et al.*, 2012). The carboxylate (-COOH) group in carboxymethyl chitosan will undergo intermolecular and intramolecular interactions with the NH_2 group to produce more NH_3^+ groups than chitosan. The NH_3^+ group will interact ionically with the negative bacterial portion (Mourya *et al.*, 2010).

The description of antibacterial activity test data for the Schiff base carboxymethyl chitosan-benzaldehyde and Schiff base carboxymethyl chitosan-salicylaldehyde is shown in **Table 2** (second experiment). In general, the results of the antibacterial activity test showed that the clear zone was bigger against *Escherichia coli* than *Staphylococcus aureus* bacteria. This shows that the sample has a higher sensitivity to *Escherichia coli* bacteria than *Staphylococcus aureus* bacteria. In the carboxymethyl chitosan-benzaldehyde and Schiff base carboxymethyl chitosan-salicylaldehyde, besides having a carboxylate group it also has an imine group ($>\text{C}=\text{N}-$), which allows the formation of carboxylate ions and iminium ions. With the addition of the polar groups, the interaction with the lipopolysaccharide layer of the outer membrane of the bacterial cell becomes more effective. From the results of the antibacterial activity test in **Table 2** (second experiment), it is known that the

Schiff carboxymethyl chitosan-salicylaldehyde base has stronger antibacterial activity than other samples, this is due to the presence of an imine group on the Schiff base. The imine group ($>\text{C}=\text{N}-$) has a lone pair on the nitrogen atom which can form a hydrogen bond with the active center of the cell. This interaction effectively disrupts the normal cell formation process (Nworie *et al.*, 2016). In addition, the presence of -OH-substituted benzene in the Schiff carboxymethyl chitosan-salicylaldehyde base framework will increase the hydrogen bonding with the active center of the cell (Verlee *et al.*, 2017).

Table 2 (the third experiment) shows the test data for the antibacterial activity of the Mn(II) -base Schiff carboxymethyl chitosan-salicylaldehyde complex. In general, the results of the antibacterial activity test showed that the clear zone was bigger against *Escherichia coli* than *Staphylococcus aureus* bacteria. From the test results, the antibacterial activity of the complex compound Mn(II) – Schiff base carboxymethyl chitosan-salicylaldehyde has stronger antibacterial activity than other samples. This is because in a complex with a more stable structure, the metal bond to the ligand can increase the antibacterial activity of the Schiff base (Lemire, 2013). Chelate which is formed from Mn metal ions and basic ligands Schiff carboxymethyl chitosan-salicylaldehyde is polar, so it will easily interact with the surface of bacterial cells which is also polar, thus disrupting metabolism and growth of bacterial cells (Wang *et al.*, 2005).

4. CONCLUSION

Mn(II)-Schiff base carboxymethyl chitosan-salicylaldehyde complex is a blackish brown solid with a yield of 59% (w / w). The Mn(II) complex-base Schiff carboxymethyl chitosan-salicylaldehyde has the greatest antibacterial activity compared to chitosan, carboxymethyl chitosan, Schiff base carboxymethyl chitosan-benzaldehyde and Schiff base carboxymethyl chitosan-salicylaldehyde against *Staphylococcus aureus* and *Escherichia coli*.

ACKNOWLEDGMENT

This research was funded by sources none other than the Diponegoro University 2020 State Budget. Number: 233-114 / UN7.6.1 / PP / 2020

18

REFERENCES

- Abdel-Monem RA, Khalil AM, Darwesh OM, Hashim AI, Rabie ST. 2020. Antibacterial properties of carboxymethyl chitosan Schiff-base nanocomposites: 29 added with silver nanoparticles. *Journal of Macromolecular Science, Part A: Pure and Applied Chemistry*. 57(2): 145–155. <https://doi.org/10.1080/10601325.2019.1674666>
- Al-Issa MA, Abbas AA, Matty FS. 2017. Synthesis and characterization of Schiff base derived from chitosan and its complexes with (Co²⁺, Ni²⁺ and Cu²⁺). *Ibn AL- Haitham Journal For Pure and Applied Science*. 29(2): 115-129.
- Ali B, Iqbal MA. 2017. Coordination complexes of manganese and their medical applications. *Chemistry Select*. 2(4): 1586–1604. <https://doi.org/10.1002/slct.201601909>
- Barbosa HFG, Attjioui M, Ferreira APG, Dockal ER, Gueddari NEEL, Moerschbacher BM, Cavaleiro ÉTG. 2017. Synthesis, characterization and biological activities of biopolymeric schiff bases prepared with chitosan and salicylaldehydes and their Pd(II) and Pt(II) complexes. *Molecules*. 22(11): <https://doi.org/10.3390/molecules22111987>
- Claudel M, Schwarte JV, Fromm KM. 2020. New antimicrobial strategies based on metal complexes. *Chemistry*. 2(4): 849–899. <https://doi.org/10.3390/chemistry2040056>
- Darmokoesoemo H, Suyanto S, Anggara S, Amenaghawon AN, Kusuma HS. 2018. Application of carboxymethyl chitosan-benzaldehyde as anticorrosion agent on steel. *International Journal of Chemical Engineering*. 2018. <https://doi.org/10.1155/2018/4397867>
- Liu XF, Guan YL, Yang DZ, Li Z, Yao KD. 2001. Antibacterial action of chitosan and carboxymethylated chitosan. *Journal of Applied Polymer Science*. 79(7): 1324–1335. [https://doi.org/10.1002/1097-4628\(20010214\)79:7<1324::AID-APP210>3.0.CO;2-L](https://doi.org/10.1002/1097-4628(20010214)79:7<1324::AID-APP210>3.0.CO;2-L)
- Fouda MMG, El-Aassar MR, Al-Deyab SS. 2013. Antimicrobial activity of carboxymethyl chitosan/polyethylene oxide nanofibers embedded silver nanoparticles. *Carbohydrate Polymers*. 92(2): 1012–1017. <https://doi.org/10.1016/j.carbpol.2012.10.047>
- Keypour H, Mahmoudabadi M, Shooshtari A, Hosseinzadeh L, Mohsenzadeh F, Gable RW. 2017. Synthesis of Mn(II) and Zn(II) complexes with new macrocyclic Schiff-base ligands containing piperazine moiety: Spectroscopic, structural, cytotoxic and antibacterial properties. *Polyhedron*. 137(II): 345–354. <https://doi.org/10.1016/j.poly.2017.02.008>
- Kurozumi S, Kiyose M, Noguchi T, Sato K. 2019. A novel hydrochloride-free chitosan oligosaccharide production method to improve taste. *International Journal of Biological Macromolecules*. 140: 109–118. <https://doi.org/10.1016/j.ijbiomac.2019.08.067>
- Malekshah RE, Shakeri F, Khaleghian A, Salehi M. 2020. Developing a biopolymeric chitosan supported Schiff-base and Cu(II), Ni(II) and Zn(II) complexes and biological evaluation as pro-drug. *International Journal of Biological Macromolecules*. 134(II): 846–861. <https://doi.org/10.1016/j.ijbiomac.2020.02.245>
- Miller SI, Salama NR. 2018. The gram-negative bacterial periplasm: S35 matters. *PLoS Biology*. 16(1): 1–7. <https://doi.org/10.1371/journal.pbio.2004935>
- Mourya VK, Inamdar NN, Swari A. 2010. Carboxymethyl chitosan and its applications. *Advanced Materials Letters*. 1(1): 11–33. <https://doi.org/10.5185/amlett.2010.3108>
- Nworio FI, Nwabue FI, Elom NI, Eluu SO. 2016. Schiff bases and schiff base metal complexes: from syntheses to applications. *J. Basic Appl. Res.*, 2: 295–305.
- Rahmani S, Mohammadi Z, Amini M, Isaie E, Taheritarigh S, Tehrani NR, Tehrani MR. 2016. Methylated 4-N,N dimethyl aminobenzyl N,O carboxymethyl chitosan as a new chitosan derivative: Synthesis, characterization, cytotoxicity and antibacterial activity. *Carbohydrate Polymers*. 149: 131–139.

- <https://doi.org/10.1016/j.carbpol.2016.04.116>
- 8 Shanmugam A, Kathiresan K, Nayak L. 2016. Preparation, characterization and antibacterial activity of chitosan and phosphorylated chitosan from cuttlebone of *Sepia kobeensis* (Hoyle, 1885). *Biotechnology Reports*. 9: 25–30. <https://doi.org/10.1016/j.btre.2015.10.007>
- 20 Silhavy TJ, Kahne D, Walker S. 2010. The bacterial cell envelope. *Cold Spring Harbor Perspectives in Biology*. 2(5): <https://doi.org/10.1101/cshperspect.a000414>
- 4 Tamer TM, Hassan MA, Omer AM, Baset WMA, Hassan ME, El-Shafeey MEA, Eldin MSM. 2016. Synthesis, characterization and antimicrobial evaluation of two aromatic chitosan Schiff base derivatives. *Access Biochemistry*. 51(10): 1721–1730. <https://doi.org/10.1016/j.procbio.2016.08.002>
- 14 Verlee A, Mincke S, Stevens CV. 2017. Recent developments in antibacterial and antifungal chitosan and its derivatives. *Carbohydrate Polymers*. 164: 268–283. <https://doi.org/10.1016/j.carbpol.2017.02.001>
- 3 Wang X, Du Y, Fan L, Liu H, Hu Y. 2005. Chitosan-metal complexes as antimicrobial agent: Synthesis, characterization and Structure-activity study. *Polymer Bulletin*. 55(1–2): 105–113. <https://doi.org/10.1007/s00289-005-0414-1>
- 2 Yin X, Chen J, Yuan W, Lin Q, Ji L, Liu F. 2012. Preparation and antibacterial activity of Schiff bases from O-carboxymethyl chitosan and para-substituted benzaldehydes. *Polymer Bulletin*. 68(5): 1215–1226. <https://doi.org/10.1007/s00289-011-0599-4>

Synthesis of Mn(II) Complexes-Carboxymethyl Chitosan Schiff Base Salicylaldehyde and Antibacterial Activity

ORIGINALITY REPORT

17%

SIMILARITY INDEX

8%

INTERNET SOURCES

14%

PUBLICATIONS

6%

STUDENT PAPERS

PRIMARY SOURCES

- | | | |
|---|---|----|
| 1 | Mickaël Claudel, Justine V. Schwarte, Katharina M. Fromm. "New Antimicrobial Strategies Based on Metal Complexes", Chemistry, 2020
Publication | 1% |
| 2 | Lal, Sohan, Sanjiv Arora, and Chetan Sharma. "Synthesis, thermal and antimicrobial studies of some Schiff bases of chitosan", Journal of Thermal Analysis and Calorimetry, 2016.
Publication | 1% |
| 3 | skemman.is
Internet Source | 1% |
| 4 | jjbs.hu.edu.jo
Internet Source | 1% |
| 5 | strathprints.strath.ac.uk
Internet Source | 1% |
| 6 | Submitted to University of KwaZulu-Natal
Student Paper | 1% |

7	Jinyu Ouyang, Zhenbiao Li, Jincheng Miao, Yongtao Wang, Langrong Hu, Xiaojuan Wang. "Antibacterial activity of carboxymethyl chitosan dialdehyde starch Schiff base and its metal complex", Research Square Platform LLC, 2022 Publication	1 %
8	www.mendeley.com Internet Source	1 %
9	Gerlane Souza de Lima, Alessandra Silva Araújo, Lúcia Raquel Ramos Berger, Ana Elizabeth Cavalcante Fai et al. "Chitosan as an antimicrobial agent to increase shelf life of foods", Elsevier BV, 2023 Publication	1 %
10	revistas.usac.edu.gt Internet Source	1 %
11	Sepideh Valizadeh, Zarrin Ghasemi, Aziz Shahrissa, Behrouz Notash, Mahtab Pirouzmand, Roya Kabiri. "Magnetic chitosan nanocomposite: As a novel catalyst for the synthesis of new derivatives of N-sulfonylamidine and N-sulfonylimidate", Carbohydrate Polymers, 2019 Publication	1 %
12	Submitted to University of Queensland Student Paper	1 %

13	rsdjournal.org Internet Source	1 %
14	notulaebotanicae.ro Internet Source	1 %
15	Usan Pathinathan Saleth Prabhakar. "Synthesis, structural elucidation of metal nanoparticles prepared from metal complexes via thermal decomposition method", Applied Surface Science Advances, 2023 Publication	<1 %
16	Hellen F.G. Barbosa, Maha Attjioui, Andrei Leitão, Bruno M. Moerschbacher, Éder T.G. Cavalheiro. "Characterization, solubility and biological activity of amphiphilic biopolymeric Schiff bases synthesized using chitosans", Carbohydrate Polymers, 2019 Publication	<1 %
17	Submitted to Higher Education Commission Pakistan Student Paper	<1 %
18	O. M. Darwesh, M. F. Eida, I. A. Matter. "Chapter 5 Environmental Nanobiotechnology: Microbial-Mediated Nanoparticles for Sustainable Environment", Springer Science and Business Media LLC, 2021 Publication	<1 %

19

Vikas Sangwan, D.P. Singh. "Macrocyclic Schiff base complexes as potent antimicrobial agents: Synthesis, characterization and biological studies", Materials Science and Engineering: C, 2019

Publication

<1 %

20

uu.diva-portal.org

Internet Source

<1 %

21

Tamer, Tamer M., Mohamed A. Hassan, Ahmed M. Omer, Walid M.A. Baset, Mohamed E. Hassan, Muhammad E.A. El-Shafeey, and Mohamed S. Mohy Eldin. "Synthesis, characterization and antimicrobial evaluation of two aromatic chitosan Schiff base derivatives", Process Biochemistry, 2016.

Publication

<1 %

22

Shunmugasundaram Gurusamy, Murugesan Sankarganesh, Radhakrishnan Nandini Asha, Alagarsamy Mathavan. "Biologically active oxovanadium(IV) Schiff base metal complex: antibacterial, antioxidant, biomolecular interaction and molecular docking studies", Journal of Biomolecular Structure and Dynamics, 2021

Publication

<1 %

23

Karl Aston, Nigam Rath, Arati Naik, Urszula Slomczynska, Otto F. Schall, Dennis P. Riley.

<1 %

"Computer-Aided Design (CAD) of Mn(II) Complexes: Superoxide Dismutase Mimetics with Catalytic Activity Exceeding the Native Enzyme", Inorganic Chemistry, 2001

Publication

24

W Widayat, A N Annisa. "Synthesis and Characterization of ZSM-5 Catalyst at Different Temperatures", IOP Conference Series: Materials Science and Engineering, 2017

Publication

25

Submitted to Liverpool John Moores University

Student Paper

26

Submitted to University of Malaya

Student Paper

27

Weixiang Liu, Yukun Qin, Song Liu, Rong Xing, Pengcheng Li. "Synthesis and antifungal activity of slow-release pyridinylcarbonyl chitooligosaccharide copper complexes", Carbohydrate Polymers, 2022

Publication

28

Zhiwei Su, Qiming Han, Fang Zhang, Xianghong Meng, Bingjie Liu. "Preparation, characterization and antibacterial properties of 6-deoxy-6-arginine modified chitosan", Carbohydrate Polymers, 2020

Publication

<1 %

<1 %

<1 %

<1 %

<1 %

29

Baran, Talat, Tülden Inanan, and Ayfer Menteş. "Synthesis, characterization, and catalytic activity in Suzuki coupling and catalase-like reactions of new chitosan supported Pd catalyst", Carbohydrate Polymers, 2016.

Publication

<1 %

30

Gerhard Bringmann, Michael Dreyer, Johan H. Faber, Petur Weihe Dalsgaard et al. "Ancistrotanzanine C and Related 5,1'- and 7,3'-Coupled Naphthylisoquinoline Alkaloids from ", Journal of Natural Products, 2004

Publication

<1 %

31

Jinyu Ouyang, Zhenbiao Li, Jincheng Miao, Yongtao Wang, Langrong Hu, Xiaojuan Wang. "Antibacterial Activity of Carboxymethyl Chitosan Dialdehyde Starch Schiff Base and its Metal Complex", Starch - Stärke, 2023

Publication

<1 %

32

Heba E. Hashem, Ashutosh Nath, Ajoy Kumer. "Synthesis, molecular docking, molecular dynamic, quantum calculation, and antibacterial activity of new Schiff base-metal complexes", Journal of Molecular Structure, 2021

Publication

<1 %

33

Olugbenga Oludayo Oluwasina, Adeoye Sulaiman Olagboye, Ademola Boboye, Foluso

<1 %

Ganiyu Hassan. "Carboxymethyl chitosan zinc supplement: Preparation, physicochemical, and preliminary antimicrobial analysis",
Cogent Chemistry, 2017

Publication

34

glycoforum.gr.jp

Internet Source

<1 %

35

www.biorxiv.org

Internet Source

<1 %

36

Xiaohui Wang, Yumin Du, Lihong Fan, Hui Liu, Ying Hu. "Chitosan- metal complexes as antimicrobial agent: Synthesis, characterization and Structure-activity study",
Polymer Bulletin, 2005

Publication

<1 %

37

digitalcommons.usu.edu

Internet Source

<1 %

38

hltcoe.jhu.edu

Internet Source

<1 %

39

iopscience.iop.org

Internet Source

<1 %

40

jurnal.stkipppersada.ac.id

Internet Source

<1 %

41

nutraceuticals.imedpub.com

Internet Source

<1 %

www.fsjour.com

42

Internet Source

<1 %

43

"Chitosan", Polysaccharides, 2015.

Publication

<1 %

44

Carlos Henrique Michelin Beraldo, Almir Spinelli, Nico Scharnagl, Thiago Ferreira da Conceição. "New relations between modification degree, swelling and impedance in anticorrosion chitosan-derivative coatings on magnesium alloy AZ31", Carbohydrate Polymers, 2022

Publication

<1 %

45

Xiao Fei Liu, Yun Lin Guan, Dong Zhi Yang, Zhi Li, Kang De Yao. "Antibacterial action of chitosan and carboxymethylated chitosan", Journal of Applied Polymer Science, 2001

Publication

<1 %

46

Amreen Naz, Shiva Arun, Shahid Suhail Narvi, Mohammad Siraj Alam, Anu Singh, Prabha Bhartiya, P.K. Dutta. "Cu(II)-carboxymethyl chitosan-silane schiff base complex grafted on nano silica: Structural evolution, antibacterial performance and dye degradation ability", International Journal of Biological Macromolecules, 2018

Publication

<1 %

47

Mohamed A. Hassan, Tamer M. Tamer, Ahmed M. Omer, Walid M.A. Baset, Eman Abbas, Mohamed S. Mohy-Eldin. "Therapeutic potential of two formulated novel chitosan derivatives with prominent antimicrobial activities against virulent microorganisms and safe profiles toward fibroblast cells", International Journal of Pharmaceutics, 2023

Publication

<1 %

Exclude quotes Off

Exclude matches Off

Exclude bibliography Off